



ACSS/AW - Aluminum Conductor Steel Supported/AW Core

Product Description

ACSS/AW is a composite concentric-lay-stranded conductor. Aluminum-clad steel strands, either AW2 (normal strength) or AW3 (high strength), form the central core of the conductor with one or more layers of aluminum 1350-0 wire stranded around it. The aluminum-clad steel core carries most or all of the mechanical load of the conductor due to the "0" (fully annealed or soft) temper aluminum. The steel core wires are protected from corrosion by an aluminum coating.

Application

ACSS/AW is used for overhead distribution and transmission lines. It is designed to operate continuously at elevated temperatures up to 250°C without loss of strength; it sags less under emergency electrical loadings than ACSR/AW; it is self-damping if pre-stretched during installation; and its final sags are not affected by long term creep of applications requiring increased current with existing tensions and clearances, new line applications where structures can be economized because of reduced conductor sag, new line applications requiring high emergency loadings, and lines where aeolian vibration is a problem. ACSS/AW offers strength characteristics similar to ACSS, along with slightly greater ampacity and resistance to corrosion due to the aluminum-cladding of the steel core wires.

Product Data

Code Word	Size (Kcmil)	Stranding (Al/St)	Diameter (ins.)			Complete Cable	Weight Per 1000 ft (lb.)			Rated Strength (lb.)	Resistance OHMS/1000ft		Ampacity at 200°C (AMPS)
			Al	Steel	Steel Core		Al	Steel	Total		DC @20°C	AC @75°C	
Juncal/ACSS/AW	266.8	30/7	.0943	.0943	.2829	.6600	252	140	392	11200	.0589	.0723	841
Ostrich/ACSS/AW	300.0	26/7	.1074	.0835	.2506	.6800	283	110	393	9360	.0534	.0656	891
Linnet/ACSS/AW	336.4	26/7	.1137	.0885	.2654	.7200	317	123	440	10500	.0476	.0585	960
Oriole/ACSS/AW	336.4	30/7	.1059	.1059	.3177	.7410	318	177	494	14200	.0467	.0573	979
Brant/ACSS/AW	397.5	24/7	.1287	.0858	.2574	.7720	374	116	490	10400	.0407	.0501	1061
Ibis/ACSS/AW	397.5	26/7	.1236	.0962	.2885	.783	374	146	520	12400	.0403	.0496	1071
Lark/ACSS/AW	397.5	30/7	.1151	.1151	.3453	.8060	375	209	584	16700	.0395	.0486	1092
Flicker/ACSS/AW	477.0	24/7	.1410	.0940	.2819	.8460	449	139	589	12500	.0339	.0418	1195
Hawk/ACSS/AW	477.0	26/7	.1354	.1053	.316	.8580	449	175	624	14900	.0336	.0413	1207
Hen/ACSS/AW	477.0	30/7	.1261	.1261	.3783	.8830	450	251	701	20100	.0329	.0405	1231
Parakeet/ACSS/AW	556.5	24/7	.1523	.1015	.3045	.9140	524	163	687	14600	.0291	.0359	1323
Dove/ACSS/AW	556.5	26/7	.1463	.1138	.3413	.9270	524	204	728	17500	.0288	.0355	1336
Eagle/ACSS/AW	556.5	30/7	.1362	.1362	.4086	.9530	525	293	818	22900	.0282	.0348	1362
Peacock/ACSS/AW	605.0	24/7	.1588	.1058	.3175	.9530	570	177	746	15900	.0267	.0330	1397
Squab/ACSS/AW	605.0	26/7	.1525	.1186	.3559	.9660	570	222	792	19000	.0265	.0327	1411
Wood Duck/ACSS/AW	605.0	30/7	.1420	.1420	.4260	.9940	571	318	889	24400	.0260	.0320	1439
Teal/ACSS/AW	605.0	30/19	.1420	.0852	.4260	.9940	571	311	883	25000	.0260	.0320	1438
Rook/ACSS/AW	636.0	24/7	.1628	.1085	.3256	.9770	599	186	785	16700	.0255	.0314	1444
Grobeak/ACSS/AW	636.0	26/7	.1564	.1216	.3649	.9910	599	233	832	19900	.0252	.0311	1458
Scoter/ACSS/AW	636.0	30/7	.1456	.1456	.4368	1.019	600	334	935	25100	.0247	.0305	1487
Egret/ACSS/AW	636.0	30/19	.1456	.0874	.4368	1.019	600	327	928	26300	.0247	.0305	1486
Flamingo/ACSS/AW	666.6	24/7	.1667	.1111	.3333	1.000	628	195	823	17500	.0243	.0300	1489
Gannet/ACSS/AW	666.6	26/7	.1601	.1245	.3736	1.014	628	245	872	20900	.0240	.0297	1504
Stilt/ACSS/AW	715.5	24/7	.1727	.1151	.3453	1.036	674	209	883	18800	.0226	.0280	1559
Starling/ACSS/AW	715.5	26/7	.1659	.1290	.3871	1.051	674	263	936	22000	.0224	.0277	1576
Redwing/ACSS/AW	715.5	30/19	.1544	.0927	.4633	1.081	676	368	1044	29500	.0220	.0272	1605
Cuckoo/ACSS/AW	795.0	24/7	.1820	.1213	.3640	1.092	749	232	981	20900	.0204	.0252	1671
Drake/ACSS/AW	795.0	26/7	.1749	.1360	.4080	1.107	749	292	1040	24400	.0202	.0250	1688
Macaw/ACSS/AW	795.0	42/7	.1376	.0784	.2293	1.055	749	92	841	11400	.0209	.0260	1630
Tern/ACSS/AW	795.0	45/7	.1329	.0886	.2658	1.063	749	124	873	13500	.0208	.0260	1620
Condor/ACSS/AW	795.0	54/7	.1213	.1213	.3640	1.092	749	232	981	15800	.0204	.0260	1639
Mallard/ACSS/AW	795.0	30/19	.1628	.0977	.4884	1.139	751	409	1160	32900	.0198	.0245	1721
Ruddy/ACSS/AW	900.0	45/7	.1414	.0943	.2828	1.131	848	140	988	15300	.0183	.0230	1767
Canary/ACSS/AW	900.0	54/7	.1291	.1291	.3873	1.162	848	263	1111	23200	.0180	.0230	1779
Rail/ACSS/AW	954.0	45/7	.1456	.0971	.2912	1.165	899	149	1047	16200	.0173	.0218	1836
Towhee/ACSS/AW	954.0	48/7	.1410	.1097	.3290	1.175	899	190	1088	19000	.0172	.0214	1858
Cardinal/ACSS/AW	954.0	54/7	.1329	.1329	.3987	1.196	899	279	1177	24600	.0170	.0217	1848
Canvasback/ACSS/AW	954.0	30/19	.1783	.1070	.5350	1.248	901	491	1392	39400	.0165	.0205	1939
Snowbird/ACSS/AW	1033.5	42/7	.1569	.0871	.2614	1.203	973	120	1093	14800	.0161	.0202	1934
Curlew/ACSS/AW	1033.5	54/7	.1383	.1383	.4150	1.245	973	302	1275	26100	.0157	.0201	1948
Bluejay/ACSS/AW	1113.0	45/7	.1573	.1048	.3145	1.258	1048	173	1222	18900	.0148	.0088	2031
Finch/ACSS/AW	1113.0	54/19	.1436	.0861	.4307	1.292	1053	318	1372	28800	.0146	.0188	2040
Bunting/ACSS/AW	1192.5	45/7	.1628	.1085	.3256	1.302	1123	186	1309	20300	.0138	.0176	2124
Grackle/ACSS/AW	1192.5	54/19	.1486	.0892	.4458	1.337	1129	341	1470	30800	.0137	.0176	2135
Bittern/ACSS/AW	1272.0	45/7	.1681	.1121	.3362	1.345	1198	198	1396	21600	.0130	.0165	2215
Pheasant/ACSS/AW	1272.0	54/19	.1535	.0921	.4604	1.381	1204	364	1568	32800	.0128	.0165	2227
Dipper/ACSS/AW	1351.0	45/7	.1733	.1155	.3465	1.386	1272	210	1483	23000	.0122	.0156	2304
Martin/ACSS/AW	1351.0	54/19	.1582	.0949	.4745	1.424	1279	386	1665	34900	.0120	.0156	2307
Bobolink/ACSS/AW	1431.0	45/7	.1783	.1189	.3566	1.427	1348	223	1571	24300	.0115	.0148	2391
Plover/ACSS/AW	1431.0	54/19	.1628	.0977	.4884	1.465	1354	409	1764	36900	.0114	.0148	2405
Nuthatch/ACSS/AW	1510.0	45/7	.1832	.1121	.3664	1.465	1422	235	1657	25700	.0109	.0141	2476
Parrot/ACSS/AW	1510.0	54/19	.1672	.1003	.5017	1.505	1429	432	1861	38900	.0108	.0141	2491
Lapwing/ACSS/AW	1590.0	45/7	.1880	.1253	.3759	1.504	1498	248	1745	27000	.0104	.0134	2560
Falcon/ACSS/AW	1590.0	54/19	.1716	.1030	.5148	1.544	1505	455	1960	41100	.0102	.0134	2576
Chukar/ACSS/AW	1780.0	84/19	.1456	.0873	.4367	1.601	1685	327	2012	33600	.0093	.0120	2772
Mockingbird/ACSS/AW	2034.5	72/7	.1681	.1121	.3362	1.681	1926	198	2124	26500	.0082	.0109	2972
Roadrunner/ACSS/AW	2057.0	76/19	.1645	.0788	.3839	1.700	1947	253	2200	30300	.0081	.0108	3007
Bluebird/ACSS/AW	2156.0	84/19	.1602	.0961	.4806	1.762	2041	396	2437	40700	.0077	.0102	3130
Kiwi/ACSS/AW	2167.0	72/7	.1735	.1157	.3470	1.735	2051	211	2262	28200	.0077	.0104	3092
Thrasher/ACSS/AW	2312.0	76/19	.1744	.0814	.4070	1.802	2188	284	2472	34100	.0072	.0097	3235
Joree/ACSS/AW	2515.0	76/19	.1819	.0849	.4245	1.880	2380	309	2689	37100	.0066	.0091	3407

+Data based on a nominal cable manufactured in accordance with ASTM B 856.

++Resistance and ampacity based on an aluminum conductivity of 63% IACS at 20°C, and an aluminum-clad steel conductivity of 20.3%

+++Ampacity based on a 200°C conductor temperature, 25°C ambient temperature, 2ft/sec wind, in sun, with emissivity of 0.5 and a coefficient of solar absorption of 0.5 at sea level.

+++Rate strengths based on aluminum-clad steel core wire in accordance with ASTM B 502.

*Manufactured with pride in DeKalb, IL USA.

Specification Data

ASTM B-609	Aluminum 1350 round wire, annealed intermediate tempers for electrical purposes
ASTM B-502	Aluminum-clad steel core wire for aluminum conductors, aluminum-clad steel reinforced, either AW2 (normal strength) or AW3 (high strength)
ASTM B-856	Concentric-lay stranded aluminum conductors, coated steel supported (ACSS)

Source URL: <http://www.nehringwire.com/aluminum-bare-aluminum-and-acsr/acssaw-aluminum-conductor-steel-supportedaw-core>
Published on [Nehring Electrical Work Company \(http://www.nehringwire.com\)](http://www.nehringwire.com)